

2006 Phase II Bongará Abbreviated Drill Hole Assay Results

Drill Hole	Interval	Thickness Meters	Zinc (%)	Lead (%)	Silver (g/t)
A-1	26.3 - 62.45	36.15	12.84	2.69	18.45
	76.30 - 77.3	1.00	42.60	4.85	46.00
A-2	31.4 - 35.5	4.10	7.95	0.05	1.70
	53.25 - 54.8	1.55	12.53	2.76	15.86
A-3	71.8 - 74.5	2.70	16.81	4.13	27.97
A-5	28.6 - 33.82	5.22	15.04	0.66	5.73
C-3	72.85 - 77.05	4.20	5.02	0.56	4.17
	89.3 - 92	2.70	6.04	0.03	1.10
C-4	97.85 -104.65	6.80	15.98	5.03	36.51
C-5	80.2 - 82.35	2.15	8.74	7.74	37.52
D-4	78.6 - 83.85	5.25	6.37	1.25	6.29
D-5	87 - 95.2	8.20	7.57	1.27	10.31
E-1	189.3 - 191.8	2.50	25.48	0.69	9.61
E-2	144.25 - 148.6	2.60	14.82	1.22	9.06
E-3	178.4 - 181.2	2.80	22.05	6.47	47.96
E-4	180.4 -185.05	4.65	6.01	3.04	21.93
E-5	171.4 - 176.7	5.30	29.77	4.65	43.99